

VAPOR IN 120

PARNA OVIRA



SESTAVA

- 1 zgornji sloj: sloj parne ovire iz PP
- 2 spodnji sloj: netkan tekstil iz PP



TEHNIČNI PODATKI

Lastnosti	zakonodaja	vrednost	USC units
Gramatura	EN 1849-2	120 g/m ²	0.39 oz/ft ²
Debelina	EN 1849-2	0,4 mm	16 mil
Prehajanje vodne pare (Sd) ⁽¹⁾	EN 1931/EN ISO 12572	30 m	0.14 US Perm
Natezna trdnost MD/CD ⁽¹⁾	EN 12311-2	220/180 N/50 mm	25/21 lbf/in
Raztezek MD/CD ⁽¹⁾	EN 12311-2	47/68 %	-
Odpornost na pretrg z žebljem MD/CD ⁽¹⁾	EN 12310-1	160/205 N	36/46 lbf
Nepropustnost za vodo	EN 1928	v skladu z	-
Odpornost na vodno paro:			
- po umetnem staranju	EN 1296/EN 1931	v skladu z	-
- v prisotnosti alkalov	EN 1847/EN 12311-2	npd	-
Reakcija na ogenj	EN 13501-1	razred E	-
Prestopna upornost	EN 12114	<0,02 m ³ /(m ² h50Pa)	0 cfm/ft ² at 50Pa
Odpornost na visoke temperature	-	-20/80 °C	-4/176 °F
Posredna izpostavljenost UV-žarkom	-	2 tedna	-
Termična prevodnost (λ)	-	0,3 W/(m·K)	0.17 BTU/h·ft·°F
Specifična toplota	-	1800 J/(kg·K)	-
Gostota	-	pribl. 300 kg/m ³	pribl. 19 lbm/ft ³
Količnik paroprepustnosti (μ)	-	pribl. 75000	pribl. 150 MNs/g
VOC	-	ni relevantno	-

⁽¹⁾ Povprečne vrednosti, pridobljene na podlagi rezultatov laboratorijskih testiranj. Za najmanjše vrednosti si oglejte izjavo o lastnostih.

🗑 Razvrstitev odpadka (2014/955/EU): 17 02 03.

KODE IN DIMENZIJE

KODA	opis	trak	H [m]	L [m]	A [m ²]	H [ft]	L [ft]	A [ft ²]	
VV120	VAPOR IN 120	-	1,5	50	75	5	164	807	36
VV12030	VAPOR IN 120 3,0 m	-	3	50	150	10	164	1615	30